

TECHNICAL DATA

DECOFINISH

PRODUCT #1062

PRODUCT DESCRIPTION

DECOFINISH #1062 is a "New Generation" water clear, two-component aliphatic 81% solids polyurea polymer coating. Available as clear or field pigmented this unique coating provides exceptional chemical and U.V. resistance as well as handles the highest abrasion levels of any topcoat.

Packaging: Kit sizes available are 1, 3 & 15 gallons. Available in all standard Thermal-Chem colors.

ADVANTAGES

- Superior surface protection
- Extremely low odor
- VOC compliant with ALL U.S. regulations and safe to use in occupied facilities
- Unmatched working time, with rapid cure time
- Can be applied on projects with low temperatures of 40° F and is not affected by high humidity.
- Excellent abrasion resistance
- Can be field pigmented
- Can be applied up to 16 mils in a single coat

LIMITATIONS

- Do not apply to substrates below 40° F
- Check Thermal-Chem Chemical Resistance Guidelines if the area(s) are to be exposed to harsh chemicals
- Do not thin this product

PRODUCT HANDLING

Read the Material Safety Data Sheet thoroughly before use.

Warning: For professional use only. Avoid contact of uncured material with skin and eyes. Contact with skin may result in irritation. Wash skin with soap and water. If contact with eyes should occur, flush with water for 15 minutes and seek immediate medical attention.

TECHNICAL DATA

% Solids	81%
Viscosity	500-750 cps
Hardness	65-70 Shore D per ASTM D2240
Abrasion Resistance	90-95 mg. loss per ASTM D1044 Tabor Wheel @ 1000 cycles
Dry to Touch	2-3 hours at 70° F
Recoat Time	2-23 hours at 70° F (after 24 hours lightly sand product)
Open for Light Traffic	24 hours at 70° F

PRODUCT APPLICATION

Apply **DECOFINISH #1062** with a squeegee, brush, or high-quality non-shed roller. Only mix the amount of product that can be properly applied within 20-40 minutes.

Surface Preparation: Apply **DECOFINISH #1062** only to clean and sound substrates. Mechanical preparation by means of shot-blasting or diamond grinding to an ICRI CSP 2/3 is recommended (see ICRI Guideline No. 03732 for additional details).

PRODUCT AVAILABILITY

Products are manufactured and available through the Thermal-Chem Corporation, 2120 Roberts Drive, Broadview, IL 60155 U.S.A.

Tel: (800) 635-3773 | (847) 288-9090

Email: sales@thermalchem.com

Website: www.thermalchem.com

TECHNICAL DATA

DECOFINISH

PRODUCT #1062

TECHNICAL/SPECIFICATION SERVICES

Additional Product Data, complete Technical Support and Product Specifications are all available through Thermal-Chem Corporation or its local representatives.

Every reasonable precaution and effort has been taken in the manufacturer of all Thermal-Chem products to comply with the published product data. Actual product performance may vary slightly due to environmental influences and/or conditions.

LIMITED WARRANTY

Thermal-Chem Corporation warrants its product to be of good quality and will, at Thermal-Chem's sole discretion, replace or refund the original purchase price (if payment was made in accordance with Thermal-Chem's payment and credit terms) of any product proved defective or non-conforming. Satisfactory results depend not only upon quality products but also upon many factors beyond our control. **THE PARTIES AGREE THAT THE REPLACEMENT OR REFUND OF PRODUCT PAYMENT FOR DEFECTIVE PRODUCT OR NON-CONFORMING GOODS IS THE SOLE AND EXCLUSIVE REMEDY. Therefore, except for such replacement, THERMAL-CHEM CORP. MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and Thermal-Chem Corporation shall have no other liability with respect thereto, including without limitation, liability for incidental or consequential damages. Any claim regarding product defect must be received in writing within ninety (90) days from the date of shipment. No claim will be considered without such written notice or after the specified time interval. The user shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith.